

PAT-NO: JP411111070A
DOCUMENT-IDENTIFIER: JP 411111070 A
TITLE: HIGHLY BENDABLE FLAT CABLE
PUBN-DATE: April 23, 1999

INVENTOR-INFORMATION:

NAME	COUNTRY
FUKUDA, YUTAKA	N/A
TANAKA, KEIICHI	N/A
MURAO, SATOSHI	N/A

ASSIGNEE-INFORMATION:

NAME	COUNTRY
SUMITOMO ELECTRIC IND LTD	N/A

APPL-NO: JP09284298

APPL-DATE: October 2, 1997

INT-CL (IPC): H01B007/08, C22C009/06

ABSTRACT:

PROBLEM TO BE SOLVED: To provide a highly bendable characteristic by constituting it by sandwiching a rectangular conductor of material having specific elongation and tensile strength between tape insulators.

SOLUTION: ~~A rectangular conductor is composed of material having elongation not less than 7% and tensile strength not less than 35 kgf/mm², and an SNCA copper alloy containing Ni by 0.4 to 4% and Si by 0.1 to 1.0% is desirably~~ used, and the other metal such as Zn and Mn may be contained by a trace

quantity. Therefore, a thickness of the rectangular conductor can be thinned to about 0.015 mm, and it is not disconnected by sliding motion not less than 3 million times in a sliding radius of 2.5 mm. It is better to preadjust this copper alloy to draft such as elongation becomes 7% or more and tensile strength becomes 35 kgf/mm² or more by an annealing process, etc. It is desirable to previously plate this copper alloy with silver, and draft of a conductor by heat treatment is easily adjusted, and corrosion resistance and connector fitting performance are improved. A prescribed thickness film composed of a double structure such as polyimide/polyurethane is normally used as an insulator.

COPYRIGHT: (C)1999,JPO

